



ETX-1 Erosion Control Blanket

ETX-1 Single Net Excelsior Blanket

A blanket featuring 100% excelsior fiber fill with a functional longevity of 12 months but will differ with soil and climate conditions. This product meets all FHWA FP-03 requirements for a Type 2.D erosion control blanket.

Part Numbers	ETX-1-67 *ETX-1-67-G	ETX-1-100	ETX-1-133 *ETX-1-133-G	ETX-1-200	ETX-1-500	ETX-1-1000
Blanket Size	4 ft x 150 ft	8 ft x 112.5 ft	8 ft x 150 ft	16 ft x 112.5 ft	8 ft x 562.5 ft	16 ft x 562.5 ft
Rolls per Pallet	16	25	16	25	4	4
Rolls per Truck Load	832	650	416	300	104	48
Netting	Single Biaxially Oriented Net - Green/Photodegradable/Polypropylene					
Opening Size	0.5 in x 0.5 in					
Stitching Thread	Synthetic/Photodegradable					
Stitching Frequency	2 in					
Fill	100% Excelsior / *100% Green Pigmented Excelsior (non-toxic colorant)					
Packaging	Each Roll is Individually Stretched Wrapped with a Label					
Other Features	6 ft flap on end of roll					

INDEX TESTING	TEST METHOD	UNIT	ENGLISH
Mass per Unit Area	ASTM D 6475	oz / sq yd	9.6
Thickness	ASTM D 6525	mils	206
Tensile Strength	ASTM D 6818	lb/in	18.1 / 9.3
Ground Cover / Light Penetration	ASTM D 6567	%	67.7 / 32.3

Notes:

1. Soil Loss Ratio = Soil Loss Bare Soil / Soil Loss with RECP = 1 / C-Factor (Note: soil loss is based on regression analysis).
2. Permissible Velocity and Shear Stress have been obtained through large scale test programs featuring specific soil types, vegetation classes, flow conditions, anchor methods, and failure criteria. These conditions may not be relevant to every project nor can they be replicated by other manufacturers. Please contact your Erosion Tech rep for more information.
3. Design Performance Criteria for Vegetated Velocity and Shear Stress are estimated values given the typical industry results for RECP's manufactured to FHWA Type 2.D standards and with similar physical properties. The Designing Engineer is responsible for determining the suitability of this product on projects.