





ETX-2-HV Erosion Control Blanket

ETX-2-HV Double Net Excelsior Blanket

A blanket featuring 100% excelsior fiber fill with a functional longevity of 12 months but will differ with soil and climate conditions. This product meets all FHWA FP-03 requirements for a Type 2.D erosion control blanket.

| Part Numbers | ETX-2-100-HV *ETX-2-100-HV-G | ETX-2-200-HV | ETX-2-400-HV | ETX-2-800-HV | | |
|----------------------|-----------------------------------------------------------------------|------------------|---------------|----------------|--|--|
| Blanket Size | 8 ft x 112.5 ft | 16 ft x 112.5 ft | 8 ft x 450 ft | 16 ft x 450 ft | | |
| Rolls per Pallet | 16 | 16 | 4 | 4 | | |
| Rolls per Truck Load | 416 | 192 | 108 | 48 | | |
| Netting | Single Biaxially Oriented Net - Green/Photodegradable/Polypropylene | | | | | |
| Opening Size | 0.5 in x 0.5 in | | | | | |
| Stitching Thread | Synthetic/Photodegradable | | | | | |
| Stitching Frequency | 2 in | | | | | |
| Fill | 100% Excelsior / *100% Green Pigmented Excelsior (non-toxic colorant) | | | | | |
| Packaging | Each Roll is Individually Stretched Wrapped with a Label | | | | | |
| Other Features | 6 ft flap on end of roll | | | | | |

| INDEX TESTING | TEST METHOD | UNIT | ENGLISH |
|----------------------------------------------------------------------------------------|-------------|----------------------------------------------------------------------------------|---------------------------|
| Mass per Unit Area | ASTM D 6475 | oz / sq yd | 11.2 |
| Thickness | ASTM D 6525 | mils | 445 |
| Tensile Strength | ASTM D 6818 | lb/in | 12.6 / 7.9 |
| Ground Cover / Light Penetration | ASTM D 6567 | % | 85.3 / 14.7 |
| Water Absorption | ASTM D 1117 | % wt Change | 202 |
| BENCH-SCALE TESTING | TEST METHOD | Parameter | ENGLISH |
| Determination of Unvegetated RECP Ability to | | 50 mm (2 in.) / hr for 30 min. | Soil Loss Ratio = 8.51 |
| Protect Soil from Rain Splash and Associated | | 100 mm (4 in.) / hr for 30 min. | Soil Loss Ratio = 8.04 |
| Runoff Under Bench-Scale Conditions | | 150 mm (6 in.) / hr for 30 min. | Soil Loss Ratio = 7.59 |
| | ASTM D 7207 | Shear: 1.64 psf for 30 min. | Soil Loss = 198.3 g |
| Determination of Unvegetated RECP Ability to | | Shear: 2.89 psf for 30 min. | Soil Loss = 371.7 g |
| Protect Soil from Hydraulically Induced Shear Stresses Under Bench-Scale Conditions | | Shear: 3.99 psf for 30 min. | Soil Loss = 1185.0 g |
| | | Soil loss curve intercept = | 2.86 psf @ ½-in soil loss |
| Determination of Temporary Degradable RECP | ASTM D 7322 | Topsoil; Fescue (Kentucky 31); 21-day incubation; 27±2° & approximately 45±5% RH | % of Control |
| Performance in Encouraging Seed Germination | | | = 558% |
| and Plant Growth | | | (increased biomass) |
| LARGE-SCALE TESTING | TEST METHOD | UNIT | ENGLISH |
| Slope Erosion | ASTM D 6459 | C Factor | 0.027 |
| Shear Stress (Un-vegetated) | ASTM D 6460 | lb/ft^2 | 2.50 |

Notes:

- 1. Soil Loss Ratio = Soil Loss Bare Soil / Soil Loss with RECP = 1 / C-Factor (Note: soil loss is based on regression analysis).
- Permissible Velocity and Shear Stress have been obtained through large scale test programs featuring specific soil types, vegetation
 classes, flow conditions, anchor methods, and failure criteria. These conditions may not be relevant to every project nor can they be
 replicated by other manufacturers. Please contact your Erosion Tech rep for more information.
- 3. Design Performance Criteria for Vegetated Velocity and Shear Stress are estimated values given the typical industry results for RECP's manufactured to FHWA Type 2.D standards and with similar physical properties. The Designing Engineer is responsible for determining the suitability of this product on projects.







